

Vollton Full Shade	1:10 Aufhellung Reduction	Produkt Product	CI	Pigment (%)	Lichtechtheit Light fastness		Wetterechtheit Weather fastness		Dichte Density (g/ml)
					VT	AH	VT	AH	
		Weiß / White 960 LF 5	PW 6	77	8	8	5	5	2,35
		Gelb / Yellow 184 LF 5	PY 184	53	7-8	7-8	4-5	4-5	2,20
		Zitron / Citron 184 LF 5	PY 184	47	7-8	7-8	4-5	4-5	2,00
		Gelborange / Yellow Orange 184 LF 5	PY 184	52	7-8	7-8	4-5	4-5	1,95
		Gelb / Yellow 3910 LF 5	PY 42	60	8	8	5	5	1,80
		Gelb / Yellow 943 LF 5	PY 42	60	8	8	5	5	1,75
		Orange / Orange 82 LF 5	PR 82	65	8	8	5	5	2,15
		Rot / Red 111 LF 5	PR 101	67	8	8	5	5	2,10
		Rot / Red 130 LF 5	PR 101	60	8	8	5	5	2,10
		Blau/Blue 5091-1 LF 5	PB 28	55	8	8	5	5	1,90
		Türkis / Turquoise 28 LF 5	PB 28	50	8	8	5	5	2,15
		Grün / Green 50 LF 5	PG 50	66	8	8	5	5	2,10
		Grün / Green GN LF 5	PG 17	70	8	8	5	5	2,25
		IR-Schwarz / IR-Black 29 LF 5	PBr 29	65	8	8	5	5	2,50
		Schwarz / Black 33 LF 5	PBk 33	69	8	8	5	5	2,20
		Schwarz / Black 11-1 LF 5	PBk 11	62	8	8	5	5	1,90

CI = Colour Index | VT = Vollton/Full Shade | AH = Aufhellung/Reduction